Wiron®-Lot

Ni66,0Cr19,0Mo5,5Fe5,0Si3,5B [%]

C€ 0197

Instructions for use

Brazing material for non-precious alloys

Wiron®-Lot is supplied in form of rods.

Wiron®-Lot complies with ISO 9333.

This product contains Nickel

REF 52625 (4 g)

Characteristics of brazing material

According to ISO 9333 Wiron®-Lot is free of cadmium, beryllium and lead

Solidus, liquidus temperature	°C	1140, 1200
Profile		round
BEGO color-code		8 (white)
Flux	Minox	yd (REF 52530)

Indications for use: Wiron®-Lot is a nickel based brazing material for dental objects made of veneerable nickel chromium alloys. It is suitable for the brazing of crowns and bridges. Suitable for ceramic veneering.

Contraindications: No contraindications are known. However, unwanted biological reactions such as allergies to contents of the alloy or electrochemically based reactions may very rarely occur. In case of known incompatibilities and allergies to contents of the metallic material it should not be used.

Warnings: Metal dust is harmful to your health. When grinding and blasting use suitable air extraction system / ventilation at the workplace and breathing mask type FFP3-FN1491

Precautions: In case of occlusal or approximal contact with a different alloy electrochemically based reactions may very rarely occur. Safety and effectiveness in treatment of children or treatment of pregnant or nursing woman have not been established. Wiron®-Lot may influence negatively the interpretation of MRI investigations.

Adverse reactions: No adverse reactions are known. Nevertheless, the rare case of occurrence of individual reactions against single components of Wiron ${}^{\! @}\text{-}Lot\ can$ never be excluded completely. In this case, the application of Wiron®-Lot should not be continued.

Prescription device: Caution: US Federal law restricts this device to sale by or on the order of a licensed dentist.

Preparation and brazing: Surfaces for brazing should be prepared through grinding. Than produce a brazing block (e. g. out of Bellatherm, REF 51105). Isolate necessarily the veneering ceramic with wax against the brazing investment material. The brazing block must be preheated at least 10 min at 300 °C. The brazing seam should be placed in a low loaded area of the restoration if possible. The surface of the joining parts should be so large as possible (regard Bruxismn!). The joint clearence should be about 0.2 mm and is to be coated economical

with a fluxing agent like Minoxyd (REF 52530). A contact between fluxing agent and veneering ceramic must be avoided at any case, because this may cause discolorations.

The brazing material should be coated with the fluxing agent and is to placed on the brazing fit. Before the brazing temperature is reached, the whole object must be heated evenly and completely near to this temperature.

Therefor the brazing block must be - regarding the volume — heated for 3-5 min to approx. 150 °C under the working temperature (Liquidus temperature + approx. 50 °C). Than the temperature should be raised to the working temperature. This temperature should be hold

After brazing the surface has to be prepared (e. g. grinding, blasting) analogous to the instruction of use for the fused alloy.

Storage conditions: none

Limit of Liability: Except where prohibited by law, BEGO Bremer Goldschlägerei Wilh. Herbst GmbH & Co. KG will not be liable for any loss or damage arising from this product, whether direct, indirect, special, incidental or consequential, regardless of the theory asserted, including warranty, contract, negligence or strict liability.

Warranty: Whether given verbally, in writing or by practical instructions, our recommendations for use are based upon our own experience and trials and can be considered as standard values. Our products are subject to a constant further development. Therefore alterations in construction and composition are reserved.

US Labeling requirements: The device labeling meets the recommendations of FDA applicable guidence docu-

Any serious incident that has occurred in relation to Wiron®-Lot should be reported to BEGO Bremer Goldschlägerei Wilh. Herbst GmbH & Co. KG and the competent authority.



Consult instructions for use



Wilhelm-Herbst-Str. 1 · 28359 Bremen, Germany

www.bego.com

Rx only For professional use only









Catalogue number



BEGO Bremer Goldschlägerei Wilh. Herbst GmbH & Co. KG

